

Appl. No. 10/807,714
ARL 03-83

Confirmation No. 4402
Amdt. dated May 2, 2008
Reply to Office Action of January 2, 2008

RECEIVED
CENTRAL FAX CENTER

MAY 02 2008

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Please Amend the Claims as Follows:

Claims 1-12 (Canceled).

Claim 13 (currently amended): A multilayer structure for use in a device for detection of microwave, millimeter, infrared (IR), ultraviolet, X-ray or gamma radiation comprising:
a silicon based substrate; and
an epitaxial $\text{Cd}_{1-z}\text{Zn}_z\text{X}_x\text{X}'_{1-x}$ film grown on the silicon based substrate by molecular beam epitaxy from multiple material sources where the flux of each of the multiple material sources is controlled under a given set of epitaxial growth conditions including temperature, where X is a chalcogenide selected from the group consisting of S and Se; X' is a higher atomic number chalcogenide relative to X and X' is selected from the group consisting of S, Se and Te; x is a number greater than zero and less than $[[1]]$.095; and z is a number greater than or equal to ~~zero~~ .005 and less than $[[1]]$.015, such that x+z is a value less than .10;
a radiation sensing $\text{Hg}_{1-y}\text{Cd}_y\text{Te}$ layer grown on the $\text{Cd}_{1-z}\text{Zn}_z\text{X}_x\text{X}'_{1-x}$ film, the $\text{Hg}_{1-y}\text{Cd}_y\text{Te}$ layer being substantially lattice matched to the $\text{Cd}_{1-z}\text{Zn}_z\text{X}_x\text{X}'_{1-x}$ film, where y is a number between .15 and .35 such that the effects of any mismatch are insignificant to device performance and the surface defect density is less than 500 per centimeter squared.

Appl. No. 10/807,714
ARL 03-83

Confirmation No. 4402
Amdt. dated May 2, 2008
Reply to Office Action of January 2, 2008

Claim 14 (currently amended): The multilayer structure of claim 13, wherein X is Se and X' is Te, and wherein the concentration of Zn and Se approaches two percent and $x+z$ approaches .04 and the epitaxial layer is grown by substrate rotation throughout the growth process to produce lateral surface uniformity and low film dislocation density.

Claim 15 (currently amended): The multilayer structure of claim 13 ~~[[14]]~~ wherein the structure is used for the detection of long wavelength IR, $x+z$ is between 0.01 and 0.08 and y is ~~between 0.15 and 0.35~~ approximately .22.

Claim 16 (cancelled).

Claim 17 (currently amended) The multilayer structure of claim ~~[[16]]~~ 15 wherein X is Se and X' is Te.

Claim 18 (currently amended): The multilayer structure of claim 14 ~~[[16]]~~, wherein ~~x is between 0.01 and 0.08 and y is between 0.15 and 0.30~~ [[.35]], and wherein the radiation sensing layer senses IR radiation.

Claims 19-24 (cancelled).

Claim 25 (currently amended): A $\text{Cd}_{1-z}\text{Zn}_z\text{Se}_x\text{Te}_{1-x}$ film grown by molecular beam epitaxy on a silicon based substrate, where x is a number between zero and one inclusive and z is greater than zero and less than ~~one~~ or equal to .02; having an overlayer of Hg_1 .

Appl. No. 10/807,714
ARL 03-83

Confirmation №. 4402
Amdt. dated May 2, 2008
Reply to Office Action of January 2, 2008

$y\text{Cd}_y\text{Te}$ thereon for the detection of infrared (IR) radiation, wherein the $\text{Cd}_{1-z}\text{Zn}_z\text{Se}_x\text{Te}_{1-x}$ film is substantially lattice matched to the overlayer of $\text{Hg}_{1-y}\text{Cd}_y\text{Te}$.

Claim 26 (currently amended): The film of claim 25, wherein $x+z$ is between $[[0.01]]$ 0.03 and 0.08 and y ~~is between 0.15 and 0.35~~ varies within a range of approximately .2 for long wavelength IR (LWIR) to a value of .4 for short wavelength IR.

Claims 27-68 (cancelled).

Claim 69 (previously presented): A $\text{Cd}_{.97}\text{Zn}_{.03}\text{Se}_{.01}\text{Te}_{.99}$ film grown on a single crystal silicon (2 1 1) oriented based substrate, having an overlayer of $\text{Hg}_{.78}\text{Cd}_{.22}\text{Te}$ thereon, wherein the growth of the $\text{Cd}_{.97}\text{Zn}_{.03}\text{Se}_{.01}\text{Te}_{.99}$ film is substantially lattice matched to the overlayer of $\text{Hg}_{.78}\text{Cd}_{.22}\text{Te}$.

Claim 70 (new) The $\text{Cd}_{.97}\text{Zn}_{.03}\text{Se}_{.01}\text{Te}_{.99}$ film grown on a single crystal silicon (2 1 1) oriented based substrate recited in claim 69, where the $\text{Cd}_{.97}\text{Zn}_{.03}\text{Se}_{.01}\text{Te}_{.99}$ film is grown on the single crystal silicon (2 1 1) oriented based substrate utilizing CdTe (2 1 1)B face.